

## PURASORB® PG S

### Product specification data sheet

Rev. No. 1 / May 2019

**Description** PURASORB PG S is a GMP grade homopolymer of Glycolide with an inherent viscosity midpoint of 1.2 dl/g. It is supplied in the form of light yellow to tan pellets. PURASORB PG S is primarily used for wound management applications, particularly for sutures and is suitable for all commonly used polymer processing techniques.

<b>Chemical composition</b>	Polyglycolide
<b>Item</b>	1830005
<b>Molecular formula</b>	$(C_4H_4O_4)_n$
<b>Chemical name</b>	poly[1,4-dioxane-2,5-dione]
<b>CAS Registry number</b>	26202-08-4

Test	Method	Specification
Appearance	Visual test	Light yellow to tan pellets
Identity	FTIR spectroscopy	Conforms to reference
Inherent viscosity	Viscometry HFIP, 25 °C, c = 0.1 g/dl	1.0 – 1.4 dl/g
Melting range	DSC 10 °C/min	205 – 235 °C
Water	Coulometric titration	max. 0.5 %
Tin	ICP	max. 50 ppm
Residual solvent	GC, headspace	max. 0.1 %
Residual monomer	GC	max. 1 %
Elemental impurities	USP method 232	max. 10 ppm

**Packaging** PURASORB PG S can be supplied in 1 kg packages. Our standardized packaging consists out of four protective layers, an inner layer of clean room grade PE bag, an outer bag of aluminum coated polyester-PE laminate, inserted in the additional bag of PE for extra protection and shipped in sealed PE containers.

---

**Storage & Handling**

When stored in the original packaging at low temperatures (-15°C), PURASORB PG S keeps its initial properties for five years (expiry date).

Stability studies indicate that, when stored in the original packaging at room temperature, PURASORB PG S keeps its initial properties for at least one year.

Please refer to our current stability statement for most up to date information on storage stability.

Allow the material to reach room temperature before opening the packaging. After opening the original packaging PURASORB PG S is best stored in an inert atmosphere and at low temperatures (-15°C).

---