

PURASORB® PC 08

Rev. No. 0 / July 2017

Product data sheet

Description PURASORB PC 08 is a GMP grade homopolymer of ε-caprolactone with an inherent viscosity midpoint of 0.8 dl/g. It is supplied in the form of white to light tan granules. PURASORB PC 08 is primarily used for medical device applications and is suitable for all commonly used polymer processing techniques.

Specification	Test	Method	Specification
	Appearance	visual	white to light tan granules
	Identification	FTIR	conforms to reference
	Inherent viscosity	CHCl ₃ , 25°C, 0.5 g/dl	0.7 – 0.9 dl/g
	Residual monomer	GC	max. 0.5 wt. %

For each batch a certificate of analysis is provided, showing the analytical data determined in our quality control laboratory. Additional analytical data can be made available upon request.

Physical-chemical properties	Molecular formula	(C ₆ H ₁₀ O ₂) _n
	Chemical name	poly[2-oxepanone]
	CAS Registry number	24980-41-4

Packaging PURASORB PC 08 can be supplied in 1 or 5 kg packages. Normal packaging consists of an inner bag of clean room grade PE and an outer bag of aluminum coated polyester-PE laminate. The packed product is shipped in an additional bag of PE and in PE containers for added protection.

Storage & Handling When stored in the original packaging at low temperatures (-15°C), PURASORB PC 08 keeps its initial properties for five years.

Allow the material to reach room temperature before opening the packaging. After opening the original packaging PURASORB PC 08 is best stored in an inert atmosphere and at low temperatures (-15°C).